



Taiacryl Blue FBL-T 250%





Dyes Properties 染料特性

F value F 值	K value K 值	Solubility 90 °C 溶解度	Liquor ratio 浴 比	Rate of Dyeing 染色速率	Build up 上色性
0.43	3	45 g/l	◎	◎	◎

Staining on 纖維污染					
Cotton	Nylon	Wool	Rayon	Silk	Polyester
5	4~5	5	5	4	5

Exhaustion 浸染適性	Continuous 連染適性	Printing 印花適性
◎	◎	◎

Exhaustion Dyeing 浸 染





Taiacryl Blue FBL-T 250%

Washing Properties 水洗特性 (1.0 % o.w.f.)

49°C (AATCC 61 2A) 49°C 耐水洗						Water 耐水	
Acetate	Cotton	Nylon	Polyester	Acrylic	Wool	Alter 色變	Nylon 污染
5	5	5	5	5	5	5	5

60°C (M&S C4A) 60°C 耐水洗						Sea Water 耐海水	
Acetate	Cotton	Nylon	Polyester	Acrylic	Wool	Alter 色變	Nylon 污染
5	5	5	5	5	5	5	5

Color Fastness 堅牢度 (1.0 % o.w.f.)

Saliva 耐唾液		Chlorinated Water 耐氯水		Perspiration 耐汗 Acid 酸	
Alter 色變	Nylon 污染	Alter 色變	Nylon 污染	Alter 色變	Nylon 污染
5	5	5	5	5	5

Light 耐光		Rubbing 耐摩擦		Perspiration 耐汗 Alkaline 鹼	
0.25 % o.w.f.	1.0 % o.w.f.	Dry 乾	Wet 濕	Alter 色變	Nylon 污染
5	5~6	5	5	5	5

Printing Properties 印花特性

Reduction agent 還原劑 Dischargeability 拔染性		Dependence on Steaming 蒸處依存性		Dependence on Steaming Process 適用蒸處方式	
Decrolin	SnCl ₂	Temperature	Time	HPS	HTS
X	X	◎	◎	◎	◎