




Taiacryl Brilliant Red CD-4GNT

100% CDP

Exhaustion Dyeing 浸染





Dyes Properties 染料特性

pH Stability pH 安定性	Solubility 85 °C 溶解度	High Temp. 高溫適染性	Liquor ratio 浴 比	Rate of Dyeing 染色速率	Build up 上色性
4~4.5	150 g/l	120°C	◎	◎	◎

Staining on 纖維污染					
Cotton	Nylon	Wool	Acrylic	Polyester	Lycra
4~5	3~4	5	1	5	4

Exhaustion 浸染適性	Continuous 連染適性	Printing 印花適性
◎	◎	◎





Taiacryl Brilliant Red CD-4GNT 100% CDP

Washing Properties 水洗特性 (1.0 % o.w.f.)

49°C (AATCC 61 2A) 49°C 耐水洗						Water 耐水	
Acetate	Cotton	Nylon	Polyester	Acrylic	Wool	Alter 色變	Staining 污染
5	5	5	5	5	5	5	5

60°C (M&S C4A) 60°C 耐水洗						Sea Water 耐海水	
Acetate	Cotton	Nylon	Polyester	Acrylic	Wool	Alter 色變	Staining 污染
5	5	5	5	5	5	5	5

Color Fastness 堅牢度 (1.0 % o.w.f.)

Heat Setting 170°C x 45" 耐定型		Chlorinated Water 100ppm 耐氯水		Perspiration Acid 耐酸汗	
Alter 色變	Staining 污染	Alter 色變	Staining 污染	Alter 色變	Staining 污染
3~4	5	3~4	4~5	5	5

Light 耐光		Rubbing 耐摩擦		Perspiration 耐汗 Alkaline 耐鹼汗	
0.5 % o.w.f.	2.0 % o.w.f.	Dry 乾	Wet 濕	Alter 色變	Staining 污染
3~4	4	5	5	5	5

Printing Properties 印花特性

Reduction agent 還原劑 Dischargeability 拔染性		Dependence on Steaming 蒸處依存性		Dependence on Steaming Process 適用蒸處方式	
White 拔白	Color 入色	Temperature	Time	HPS	HTS
X	X	◎	◎	◎	X