

T & T LABORATORY TECHNICAL DATA

Chief	Tester	Date	Data No.
鍾招平	張雅屏	113.05.17C4050031	

Proposal

Material:

Acrylic 100% 28/1 (T&T)

Process:

Dyeing (100°C X 30')

Recipe:

Pantone 13-1023


Taiacryl Golden Yellow BRT 200%

0.019%

Taiacryl Red 2GL-T 200%

0.0057%

PH4



Washing Fastness Test(AATCC2A)

Before After

T&T MIX A)



T & T INDUSTRIES CORPORATION

NO 3.KUO-CHIEN 1ST RD.KUAN-YIN IND. ZONE, TEL : (03)4831666
 TAO-YUAN HSIEN,TAIWAN FAX : (03)4832666

Standard Name 178 of 229

PANTONE 13-1023

Instrument Setup: %R USAV SCI UV Inc

Batch Name 3 of 72


Acrylic Mix A

Date: 14-May-24 Time: 13:32:25

Instrument Setup: %R LAV SCI UV Inc

CMC DE Pass/Fail Tolerance: 0.50

l:c Ratio: (2.00 1.00)



Batch Name

Ill/Obs

DL*

Da*

Db*

CIE DE

DL*/ISL

DC*/cSC

DH*/SH

CMC DE

Status

Strength

Acrylic Mix A

D65 10 Deg

0.04

0.10

-0.36

0.37

0.01

-0.12

-0.35

0.37

Pass

97.50

Acrylic Mix A

F11 10 Deg

0.28

-0.42

-0.29

0.58


0.10

-0.21

0.26

0.35

Pass



Batch Name

Acrylic Mix A
 Acrylic Mix A

Metamerism

0.58

Color Comments

lighter
 lighter

more red more blue
 more green more blue

PANTONE 13-1023

Acrylic Mix A