

# T & T LABORATORY TECHNICAL DATA

Chief	Tester	Date	Data No.
鍾招平	張雅屏	113.05.17C40	50033

Proposal

Material:

Cotton 100% (T&T)


Process: Dyeing (100°CX30') → Dyefix DR119 3% (60°CX20')  
PH=5

Recipe:

Pantone 13-1023

Tairus Supra Orange 2GL-T	0.0302%
Tairus Scarlet F2G-T	0.014%
Tairus Blue 2GL-T	0.0003%

Na<sub>2</sub>SO<sub>4</sub> 5g/l



Washing Fastness Test(AATCC2A)

Before      After

T&T MIX A)



CA CO PA PES PAN WO

# T & T INDUSTRIES CORPORATION

NO 3.KUO-CHIEN 1ST RD.KUAN-YIN IND. ZONE, TEL : (03)4831666  
 TAO-YUAN HSIEN, TAIWAN FAX : (03)4832666

Standard Name 178 of 229

PANTONE 13-1023

Instrument Setup: %R USAV SCI UV Inc

Batch Name 15 of 72


Cotton Mix A

Date: 15-May-24 Time: 11:01:37


Instrument Setup: %R LAV SCI UV Inc

CMC DE Pass/Fail Tolerance: 0.50

l:c Ratio: ( 2.00 1.00)



Batch Name	Ill/Obs	DL*	Da*	Db*	CIE DE	DL*/ISL	DC*/cSC	DH*/SH	CMC DE	Status	Strength
Cotton Mix A	D65 10 Deg	-0.26	0.21	-0.04	0.34	-0.10	0.04	-0.25	0.27	Pass	101.82
Cotton Mix A	F11 10 Deg	-0.17	0.33	0.09	0.38	-0.06	0.11	-0.28	0.31	Pass	



PANTONE 13-1023

----- Cotton Mix A

### Batch Name

Cotton Mix A  
 Cotton Mix A

### Metamerism

0.20

### Color Comments

darker darker more red more blue more yellow